

**TYPICAL PROPERTIES OF TOYOLAC 100 X01**

Typical Properties	Test Method	Test Conditions	SI Unit	Typical Value
<b>Physical</b>				
Specific Gravity	ASTM D792		-	1.04
Water Absorption	ASTM D570	23°C x 24 hours	%	0.3
Mould Shrinkage	ASTM D955		%	0.4 - 0.6
<b>Rheological</b>				
Melt Flow Rate	ISO 1133	220°C / 10 kg	g/10 min	15
<b>Mechanical</b>				
Tensile stress at yield	ASTM D638	at 5 mm/min	MPa	41
Tensile strain at break	ASTM D638	at 5 mm/min	%	40
Flexural Strength	ASTM D790	at 3 mm/min	MPa	63
Flexural Modulus	ASTM D790	at 3 mm/min	MPa	1960
Rockwell Hardness	ASTM D785	R scale	-	105
<b>Impact</b>				
Izod Impact Strength, notched	ASTM D256	12.7 x 62.5 x 12.7 <sup>t</sup> mm (23°C)	J/m	294
	ASTM D256	12.7 x 62.5 x 12.7 <sup>t</sup> mm (0°C)	J/m	196
	ASTM D256	12.7 x 62.5 x 12.7 <sup>t</sup> mm (-30°C)	J/m	137
Izod Impact Strength, notched	ASTM D256	12.7 x 62.5 x 3.2 <sup>t</sup> mm (23°C)	J/m	314
	ASTM D256	12.7 x 62.5 x 3.2 <sup>t</sup> mm (0°C)	J/m	226
	ASTM D256	12.7 x 62.5 x 3.2 <sup>t</sup> mm (-30°C)	J/m	157
<b>Thermal</b>				
HDT (Unannealed) 127 x 12.7 x 12.7 <sup>t</sup> mm	ASTM D648	1.82 MPa Loading, 18.56 kg/cm <sup>2</sup>	°C	91
HDT (Unannealed) 127 x 12.7 x 6.4 <sup>t</sup> mm	ASTM D648	1.82 MPa Loading, 18.56 kg/cm <sup>2</sup>	°C	85
Thermal Conductivity	ASTM C177		W/K.m	0.15
Coefficient of Linear Thermal Expansion	ASTM D696		mm/mm°C	7.6 x 10 <sup>-5</sup>
<b>Flammability</b>				
Flammability	UL 94		-	HB
<b>Electrical</b>				
Specific Surface Resistivity	ASTM D257	at 23°C	ohm	>10 <sup>16</sup>
Specific Volume Resistivity	ASTM D257	at 23°C	ohm.cm	>10 <sup>16</sup>
Dielectric Strength	ASTM D149	Short Time	KV/mm	24
Dielectric Constant	ASTM D150	1000 Hz	-	3.1
Power Factor	ASTM D150	1000 Hz	-	6.5 X 10 <sup>-3</sup>

Toray Plastics Malaysia Sdn. Bhd. (Head Office)  
 2628, MK1 SPT, Lorong Perusahaan 4 FIZ, Prai, 13600, Penang, Malaysia  
 Tel: 604-3988088 Fax: 604-3908975  
 Email : [sales.tpm@toray.com.my](mailto:sales.tpm@toray.com.my)  
[www.torayplastics.com](http://www.torayplastics.com)